

Technical Data

Hardtop XPL



Product description

A two-pack high solid, semiflat aliphatic polyurethane topcoat with excellent gloss and colour retention.

Recommended use

As a topcoat over most epoxy systems where a durable, weather-resistant finish is required in a wide range of aggressive atmospheres.

Film thickness and spreading rate

	Minimum	Maximum	Typical
Film thickness, dry (µm)	40	80	60
Film thickness, wet (µm)	70	140	100
Theoretical spreading rate (m ² /l)	14,5	7,3	9,7

Physical properties

Colour	According to colour card and Multicolor tinting system (MCI)
Solids (vol %)*	58 ± 2
Flash point	28°C ± 2 (Setaflash)
VOC	3,1 lbs/gal (372 gms/ltr) USA-EPA Method 24 375 gms/ltr UK-PG6/23(97). Appendix 3
Gloss	Semiflat
Gloss retention	Excellent
Water resistance	Very good
Abrasion resistance	Very good
Solvent resistance	Good
Chemical resistance	Very good
Flexibility	Very good

*Measured according to ISO 3233:1998 (E)

Note: Gloss may vary with application method and applied thickness.

Surface preparation

All surfaces should be clean, dry and free from contamination. The surface should be assessed and treated in accordance with ISO 8504.

Coated surfaces

Clean, dry and undamaged compatible primer. Please contact your local Jotun office for more information.

Other surfaces

The coating may be used on other substrates. Please contact your local Jotun office for more information.

Condition during application

The temperature of the substrate should be minimum 0°C and at least 3°C above the dew point of the air, temperature and relative humidity measured in the vicinity of the substrate. Good ventilation is usually required in confined areas to ensure proper drying.

Application methods

Spray	Use airless spray or conventional spray
Brush	Recommended for stripe coating and small areas, care must be taken to achieve the specified dry film thickness.
Roller	May be used for small areas.

Application data

Mixing ratio (volume)	10:1
Mixing	10 parts Hardtop XPL Comp. A (Base) to be mixed thoroughly with 1 part Hardtop XP, Comp. B (Curing agent) by powered mechanical equipment. Mix complete units only, do not part mixing of this product.
Pot life (23°C)	1,5 hours
Thinner/Cleaner	Jotun Thinner No. 10
Guiding data airless spray	
Pressure at nozzle	15 MPa (150 kp/cm ² , 2100 psi)
Nozzle tip	0.38-0.46 mm (0.015-0.017")
Spray angle	40-80°
Filter	Check to ensure that filters are clean.

Drying time

Drying times are generally related to air circulation, temperature, film thickness and number of coats, and will be affected correspondingly. The figures given in the table are typical with:

- * Good ventilation (Outdoor exposure or free circulation of air)
- * Typical film thickness
- * One coat on top of inert substrate

Substrate temperature	5°C	10°C	23°C	40°C
Surface dry	7 h	5 h	3 h	0,5 h
Through dry	24 h	12 h	5 h	3 h
Cured	21 d	14 d	7 d	3 d
Dry to recoat, minimum	24 h	12 h	5 h	3 h
Dry to recoat, maximum ¹				

1. The surface should be dry and free from any contamination or chalking prior to application of the subsequent coat.
2. Early exposure to condensation (high humidity, low temperature) may cause colour and/or gloss variations.

The given data must be considered as guidelines only. The actual drying time/times before recoating may be shorter or longer, depending on film thickness, ventilation, humidity, underlying paint system, requirement for early handling and mechanical strength etc. A complete system can be described on a system sheet, where all parameters and special conditions could be included.

Typical paint system

Jotacote Universal	1 x 150 µm	(Dry Film Thickness)
Hardtop XPL	1 x 60 µm	(Dry Film Thickness)
Jotamastic 87	1 x 150 µm	(Dry Film Thickness)
Hardtop XPL	1 x 60 µm	(Dry Film Thickness)

Other systems may be specified, depending on area of use

Storage

The product must be stored in accordance with national regulations. Storage conditions are to keep the containers in a dry, cool, well ventilated space and away from source of heat and ignition. Containers must be kept tightly closed.

Handling

Handle with care. Stir well before use.

Packing size

20 litre unit: 18,2 litres Hardtop XPL Comp. A in a 20 litre container and 1,8 litres Hardtop XP, Comp. B (curing agent) in a 3 litre container or

5 litre unit: 4,55 litres Hardtop XPL Comp. A in a 5 litre container and 0.45 litre Hardtop XP, Comp. B (curing agent) in a 1 litre container

Health and safety

Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Do not breathe or inhale mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately.

For detailed information on the health and safety hazards and precautions for use of this product, we refer to the Material Safety Data Sheet.

DISCLAIMER

The information in this data sheet is given to the best of our knowledge based on laboratory testing and practical experience. However, as the product can be used under conditions beyond our control, we can only guarantee the quality of the product itself. We also reserve the right to change the given data without notice. Minor product variations may be implemented in order to comply with local requirements.

If there is any inconsistency in the text the English (UK) version will prevail.

Jotun is a World Wide company with factories, sales offices and stocks in more than 50 countries. For your nearest local Jotun address please contact the nearest regional office or visit our website at www.jotun.com

ISSUED 2 JULY 2012 BY JOTUN
THIS DATA SHEET SUPERSEDES THOSE PREVIOUSLY ISSUED