

Technical Data

Jotafloor Screed



Product description

Jotafloor Screed is a high performance, trowel applied, three component, solvent free epoxy floor coating offering exceptional strength characteristics, resistance to a range of chemicals, and superior abrasion/wear properties. Generally applied at 5 mm thickness and above. (Seek advice from Jotun Technical Department)

Recommended use

The high strength impervious finish makes Jotafloor Screed ideal for heavy industrial areas such as:

- Steelworks
- Engineering plants
- Chemical production areas
- Oil refineries
- Dairies

Also ideally suited where heavy traffic is expected or a durable non-slip finish is required. Jotafloor Screed may be overcoated with Jotafloor Topcoat or Jotafloor Coating if different colours are required. Jotafloor Screed exhibits very high bond strength and adhesion characteristics making it an ideal repair material for concrete and floor joint edges.

Film thickness and spreading rate

	Minimum	Maximum	Typical
Film thickness, dry (μm)	4000	6000	5000
Film thickness, wet (μm)	4000	6000	5000
Theoretical spreading rate (m^2/l)	0,25	0,17	0,2

Comments

Jotafloor Screed can be applied at higher thicknesses to suit specific requirements. Request further information from Jotun Technical Department.

Physical properties

Colour	Colour of the graded aggregate
Solids (vol %)*	98 ±
Flash point	>100°C (Setaflash)
VOC	1 gms/ltr UK-PG6/23(97). Appendix 3
Water resistance	Excellent
Abrasion resistance	Excellent
Solvent resistance	Excellent
Chemical resistance	Excellent Check chemical resistance values on Jotafloor chemical resistance chart.

*Measured according to ISO 3233:1998 (E)

Surface preparation

All concrete damaged by exposure to chemicals, contaminated by any substance or unsound in any way, shall be removed to expose sound concrete.

Other surfaces

Concrete surface preparation by using dust free captive blasting units, grinding equipment, sand blasting or high pressure water jetting is critical to achieving the right surface profile prior to paint application. Contact your local Jotun office for more information.

The coating may be used on other substrates. Please contact your local Jotun office for more information.

Condition during application

The temperature of the substrate should be minimum 12°C (preferably 15°C) and at least 3°C above the dew point of the air, temperature and relative humidity measured in the vicinity of the substrate. The moisture in the concrete should not exceed 4 % (by weight). The coating should not be exposed to oil, chemicals or mechanical stress until fully cured.

Application methods

Other Nylon or steel trowel.

Application data

Mixing ratio (volume)	1.3:0.65:9.43 (25 kgs)
Mixing	1.3 litres Comp. A (base) to be mixed thoroughly with 0.65 litre Comp. B (curing agent) before adding 25 kg/9.43 litres graded aggregates. NO PART MIXING. Mix the resin and curing agent well before adding the aggregate. A forced action drill and appropriate mixing paddle should be used.
Pot life (23°C)	25 min. (Comp. A + Comp. B only), 40 min. (mix. with aggregate). (after poured on the floor)
Cleaner	Jotun Thinner No. 17 or fresh water.

Note

It is essential to apply Jotafloor Screed onto Jotafloor Screed Primer whilst the primer is still "tacky". See separate Technical Data Sheet.

If the surface is porous or absorbant, such surface should be sealed with primer first. Once sealed well the recommended system can be applied

This product should be applied by a trained specialist. Jotun can offer a list of Licensed Applicators on request to your local Jotun office.

Drying time

Drying times are generally related to air circulation, temperature, film thickness and number of coats, and will be affected correspondingly. The figures given in the table are typical with:

- * Good ventilation (Outdoor exposure or free circulation of air)
- * Typical film thickness
- * One coat on top of inert substrate

Substrate temperature	15°C	23°C	40°C
Surface dry	10 h	6 h	3 h
Through dry	16 h	10 h	4 h
Cured	8 d	7 d	4 d
Dry to recoat, minimum	16 h	10 h	4 h
Dry to recoat, maximum ¹	96 h	96 h	48 h

- The surface should be free from chalking and contamination prior to application. If the maximum dry to recoat time is exceeded, please contact Jotun Paints for advice.

The given data must be considered as guidelines only. The actual drying time/times before recoating may be shorter or longer, depending on film thickness, ventilation, humidity, underlying paint system, requirement for early handling and mechanical strength etc. A complete system can be described on a system sheet, where all parameters and special conditions could be included.

Typical paint system

Jotafloor Screed Primer	1 x 150 µm	(Dry Film Thickness)
Jotafloor Screed	1 x 5000 µm	(Dry Film Thickness)
and eventually		
Jotafloor Topcoat	1 - 2 x 50 µm	(Dry Film Thickness)

Other systems may be specified, depending on area of use

Test Certificates

- Determination of Compressive Strength - ASTM C579
- Determination of Tensile Strength - ASTM C307
- Determination of Flexural Strength - ASTM C580
- Determination of Bond strength to host concrete - BS 1881 : Part 207
- Determination of Crack Bridgeability - ASTM C884
- Determination of Rapid Chloride Permeability - AASHTO T277
- Determination of Water Permeability - DIN 1048
- Determination of Acid or Alkali Reaction - ASTM D543
- Determination of Water or Salt Spray Test - N.F.C. Standard
- Determination of Impact Resistance - ISO 6272
- Determination of Taber Abrasion (1,000 Cycles) - ASTM D4060

Storage

The product must be stored in accordance with national regulations. Storage conditions are to keep the containers in a dry, cool, well ventilated space and away from source of heat and ignition. Containers must be kept tightly closed.

Handling

Handle with care. Stir well before use.

Packing size

1.3 litres Comp. A (base) in a 3 litre container and 0.65 litre Jotafloor Screed, Comp. B (curing agent) in a 1litre container and 9.43 litres Comp C (graded aggregate).

Health and safety

Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Do not breathe or inhale mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately.

For detailed information on the health and safety hazards and precautions for use of this product, we refer to the Material Safety Data Sheet.

DISCLAIMER

The information in this data sheet is given to the best of our knowledge based on laboratory testing and practical experience. However, as the product can be used under conditions beyond our control, we can only guarantee the quality of the product itself. We also reserve the right to change the given data without notice. Minor product variations may be implemented in order to comply with local requirements.

If there is any inconsistency in the text the English (UK) version will prevail.

Jotun is a World Wide company with factories, sales offices and stocks in more than 50 countries. For your nearest local Jotun address please contact the nearest regional office or visit our website at www.jotun.com

ISSUED 6 JUNE 2013 BY JOTUN
THIS DATA SHEET SUPERSEDES THOSE PREVIOUSLY ISSUED